

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Ferrorep[®]

Anticorrosive coating

Fields of application

Anticorrosive coating for steel reinforcement of concrete elements in repair works. It protects from corrosion the concrete reinforcement which is expected to work in high humidity condition. It has very strong adhesion on metals, offering durability against extreme weather conditions and UV radiation. It is also suitable for strong bonding of old to new concrete.

Properties

- Very strong adhesion
- Anticorrosive protection
- Durability against extreme weather conditions
- High coverage
- It is CE certified, according to EN 1504-7.

Technical characteristics

Consumption	50-70gr/linear meter of reinforcement element for 2 layers and thickness 1mm (depending on the rod's diameter) and 1,3-1,5kg/m ² for bonding old to new concrete.
Water requirement	35% by weight
Pot life	60 min. at +25°C
Density (EN ISO 2811-1:12011)	1,54g/cm ³
Glass temperature Tg (EN 12614:2004)	318,0 K

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Ferrorep[®]

Instructions for use

Substrate should be clean, dry and free from dust, oil, grease, or any poorly adhering material. Add 1 Kg **Ferrorep[®]** into 350 gr water and stir very well for 3 minutes with low-revolution stirrer until obtaining a uniform mass without lumps. Leave the can for 5 minutes before the application. **Ferrorep[®]** is applied using a brush in two layers. Each layer is applied once the previous one has dried.

Notes

- Do not use the product at temperatures lower than +5°C.
- Total hardening and final properties occurrence: 7 days after the application.

Cleaning of tools

Use plenty of water immediately after application.

Αφαίρεση κηλίδων

Όσο είναι νωπό με νερό. Αν έχει σκληρυνθεί με μηχανική αφαίρεση.

Color

Terracotta

Packing

1 Kg, 4 kg and 20 kg in plastic container.


Storage stability

At least 12 months in its original sealed container, in an absolutely dry place protected from frost and humidity.

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Ferrorep[®]



1922

NEOTEX S.A.

V. Moira str., P.O. Box 2315
GR 19600 Industrial Area Mandra, Athens, Greece

14

1922-CPR-0386
DoPNo. Ferrorep /4950-06

EN 1504-7

Ferrorep

Reinforcement corrosion protection

Active coating

Corrosion protection	:	Pass
Glass transition temperature	:	> +40°C
Shear adhesion of coated steel in concrete	:	Pass
Dangerous substances	:	comply with 5.3