

**READY-TO-USE SKIMCOAT RENDERING COATING
INTERIOR WALLS AND CEILINGS
THICKNESS 0.3 - 4MM.**

102
INTERIOR SkimCoat

R E N D E R I N G

CHARACTERISTICS

- **Ready-to-use and easy application**
- **White smooth finish**
- **Excellent trowel-ability on application**
- **Possible to be painted in 24 Hrs.
(With or without primer)**
- **Cost and time saving**

LANKO



COVERAGE

0.5 – 1.5 Kg/m²/mm.
(Depend on the quality of substrate)

PACKAGING

- 5KG Bucket
- 20KG Bucket

STORAGE

1 Year from date of manufacture if stored in unopened original packing in dry, frost-free conditions.

DESCRIPTION

102 INTERIOR SkimCoat is a smoothing rendering paste. It's ready-to-use formula for repairing surface defects in concrete or render. A smooth surface is obtained by eliminating blemishes such as grooves, seams, fine cracks and rock pockets.

USES

Can be applied for interior walls and ceilings.

Permissible substrates

- Concrete
- Rendering
- Precast concrete
- Gypsum board

Possible covering materials

- Thick plastic coating
- Paint
- Wallpaper
- Fabric

SPECIFICATIONS

- White, hydraulic binder-free paste
- Composition : Synthetic resins, mineral filler and admixtures
- Particle size : 0 to 0.1 mm.
- Paste density : 1.8
- pH : 9±0.5

Bonding strength (MPa) at 28 days* on unsurfaced concrete

1 mm. thickness : 0.93 MPa

3 mm. thickness : 0.71 MPa

*average laboratory values provided as a general guide.

INSTRUCTIONS

Substrate preparation

- The substrate must be clean, sound, dust-free and without any traces of oil, laitance curing compound, etc.
- Over-plus, seams and rock pockets exceeding 3mm must be treated prior to application.

Product preparation

- Ready-to-use paste. No water must be added.

Application

- Apply small quantities of LANKO 102 INTERIOR SkimCoat with a stainless steel trowel.
- Wash the blade of the tool regularly in order to remove hardened residues. Never return the product to the bucket.
- Two separate coats must be applied for successful resurfacing (First layer as a primer to fill up all minor defects).
- Allow 2 hours at 20°C between coats.
- Pre-covering curing time 24 – 48 hours (depending on application thickness covering material and atmospheric conditions).

PRECAUTIONS

- Do not apply to a damp or frozen substrate
- Do not use in freezing conditions
- Do not add any water
- Do not cover with a hydraulic binder-based mortar
- Do not mix with any other product

The information provided in this document results from our knowledge of the products and our experience. On-site results may vary, in particular according to the product application methods adopted. Where application methods not representative test before using the products. The above-mentioned information in no way constitutes a warranty relative to the use of the products. Our general terms and conditions of sale shall prevail. In any event, on the information provided in this document. Prior to application, customers and users are requested to check that they have the latest version of this document.



www.parexgroup.co.th

ParexGroup Company Limited

183 Regent House Building, Rajdamri Road, Lumpini, Pathumwan, Bangkok 10330 Tel. 66 (0) 2651 9838 Fax. 66 (0) 2651 8003

