

**SKIM COAT PLUS
READY TO USE SKIM RENDERING COATING
INTERIOR AND EXTERIOR WALLS AND CEILINGS
THICKNESS 0.3 - 4 mm.**

103
LANKOWALL

R E N D E R I N G

LANKO



CHARACTERISTICS

- **Thickness 0.3 to 4.0 mm**
- **Ready to use and easy application**
- **Perfectly white smooth finish.**
- **Excellent trowelability on application.**
- **Possible to be exposed or painted (with or without primer)**
- **Good weather resistance**
- **Cost and time saving**

COVERAGE

0.5–1.5 kg /m²/mm.
(Depend on the quality of substrate)

PACKAGING

- 5 kg Bucket
- 25 kg Bucket

STORAGE

1 year from date of manufacture if stored in unopened original packing in dry, frost-free conditions.

DESCRIPTION

103 LANKOWALL is a skim smoothing rendering paste. It's ready to use formula for repairing surface defects in concrete or render.

A smooth surface is obtained by eliminating blemishes such as grooves, seams, fine cracks and rock pockets.

USES

Can be applied for Interior and exterior walls.

Permissible substrates

Interior / exterior

- Shuttered concrete
- Reinforced concrete shell-work
- Concrete Soffits
- Precast concrete

Interior only

- Light-weight concrete block (Apply 751Lankolatex mix with water by ratio 1:2 as a primer layer)
- Bricks
- Gypsum block, gypsum board.
- Gypsum (Consult ParexDavco Technical Service for further advice in this situation)

Possible covering materials

- Thick plastic coating
- Paint
- Wallpaper
- Fabric
- Bonded plastic coverings
- Ceramic covering using a cement-free adhesive (interior only, maximum format 1200 cm²)

SPECIFICATIONS

- White, hydraulic binder-free paste
- Composition : synthetic resins, mineral filler and admixtures.
- Particle size : 0 to 0.1mm
- Paste density : 1.8
- pH : 9 ± 0.5

Bonding strength (Mpa) at 28 days* on unsurfaced concrete

1mm thickness : 2 MPa

3mm thickness : 1.5 MPa

* average laboratory values provided as a general guide.

INSTRUCTIONS

Substrate preparation

- The substrate must be clean, sound, dust-free and without any traces of oil, laitance, curing compound etc....
- Overplus, seams and rock pockets exceeding 3mm must be treated prior to application.

Product preparation

- Ready-to-use paste. No water must be added.

ISO 9001
ISO 14001
OHSAS 18001
BUREAU VERITAS
Certification



www.parexgroup.co.th

ParexGroup Company Limited

183 Regent House Building, Rajdamri Road, Lumpini, Pathumwan, Bangkok 10330 Tel. 66 (0) 2651 9838 Fax. 66 (0) 2651 8003

PAREXGROUP
Building expertise, together



Application

- Apply small quantities of 103 LANKOWALL with a stainless steel trowel.
- Wash the blade of the tool regularly in order to remove hardened residues. Never return the product to the bucket.
- Two separate coats must be applied for successful resurfacing. (First layer as a primer to fill up all minor defects).
- Allow 2 hours at 20 °C between coats. Pre-covering curing time 24 – 48 hours (depending on application thickness, covering material and atmospheric conditions).

PRECAUTIONS

- Do not apply to a damp or frozen substrate. Do not use in freezing conditions.
- Do not add any water.
- Do not cover with a hydraulic binder-based mortar.
- Do not mix with any other product