

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

## Neolastik<sup>®</sup> 1K

### Elastic fiber reinforced cementitious waterproofing material

#### Fields of Application

One component elastic cementitious material suitable for:

- waterproofing applications with high elasticity on terraces, balconies under tiles and exposed surfaces, such as flat roofs, exterior walls etc
- Underground surfaces of buildings, interior or exterior.

#### Properties/ Advantages

- Offers high elasticity, impermeability and protection to every vertical or horizontal construction surface, that is subjected to vibrations, contractions – expansions or chemical substances.
- Remarkable adhesion on numerous substrates, like concrete, cement slurries, bricks, metals, gypsum boards, polysterene, mosaic and ceramic.
- Prevents metallic reinforcements corrosion, while enhances adhesion of cement on to the reinforcement.
- Resistant at low temperatures and snow/frost melting
- Water vapor-permeable, protects from concrete carbonization
- Resistant to hydrostatic pressure
- Economic and easy to apply, even from un-trained personnel
- Bridges cracks, pores and thin joints
- Protects from underground radon and chloride migration
- Environmentally friendly
- Certified with CE (EN 1504-2)

#### Technical characteristics

<b>Colour</b>	Grey
<b>Consumption</b>	2-3kg/m <sup>2</sup> for 2 layers
<b>Water permeability (EN 1062-3:2008)</b>	0,005kg/(m <sup>2</sup> xh <sup>0.5</sup> )
<b>Bonding strength (EN 1542)</b>	>1,5 N/mm <sup>2</sup>

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX<sup>®</sup> SA .It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX<sup>®</sup> SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

## Neolastik<sup>®</sup> 1K

Water vapor permeability V (EN 7783-1:1999)	2,1g/m <sup>2</sup> d <sup>-1</sup>
Maximum application thickness per layer	1mm
Maximum application thickness of final application	3mm
Mixing ratio	5-6 lt water per 20Kg of <b>Neolastik 1K</b>
Working time/Pot life (+25°C)	45 minutes
Temperature of application	+5°C to +35°C
Drying time (+25°C)	6 hours

These times are prolonged by low temperatures and moisture, while shortened by higher ones.

### Instructions for use

#### Surface preparation:

Surfaces must be dry, clean from dust, dirt, greasy substances and homogeneous. Cavities or other imperfections must be repaired with **Neorep<sup>®</sup>** and **Revinex<sup>®</sup>**.

#### Mixture preparation:

Add gradually component A (powder) into the water and mix using a low speed mechanical mixer, until a perfectly homogenous mix is obtained.

#### Application:

Apply the mixture by brush, roller, preferably in at least 2 layers of 1 mm thickness each, or spatula with 2 mm thickness of each layer. The mixing ratio for application by brush is 6lt water for 20kg **Neolastik<sup>®</sup> 1K**. For application by trowel the ratio is 5lt water for 20kg powder. For thicker coatings and resistance to tearing use fiberglass mesh **Gavazzi<sup>®</sup> 0059-A** between the 2 coatings, while the first is still wet.

### Notes

- Never apply when rain is forecasted.
- Allow **Neolastik<sup>®</sup> 1K** to dry between 5 and 8 days, before applying tiles or other coatings.

**ATHENS:** V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

**THESSALONIKI:** 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

## Neolastik<sup>®</sup> 1K


<b>Packing</b>	20kg carton bags
<b>Storage stability</b>	2 years, sealed in its original packing, protected from frost and direct exposure to sun, between +5 °C and +35°C.
<b>Cleaning of tools</b>	Clean all tools and application equipment with water immediately after use. Hardened material can only be mechanically removed.



ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

## Neolastik® 1K



1922

NEOTEX S.A

V. Moira str., P.O. Box 2315  
GR 19600 Industrial Area Mandra, Athens, Greece

16

1922-CPR-0386  
DoP No. Neolastik 1K

EN 1504-2

Neolastik 1K

Surface protection system for concrete

Coating

Water vapour permeability	:	Class II
Capillary absorption and permeability to water	:	$W < 0,1 \text{ kg/m}^2 \text{ h}^{0,5}$
Adhesion strength	:	$\geq 1,5 \text{ N/mm}^2$
Permeability to CO <sub>2</sub>	:	$s_D > 50 \text{ m}$
Reaction to fire	:	Euroclass F
Dangerous substances	:	comply with 5.3